



7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвЭВнгд-150 1x1600 ТУ У 31.3-00214534-060:2011

Power cables with aluminium conductor, flame-retardant, with XLPE and with PVC compound outer sheath and with low smoke and gas emission

For the cable of this mark correspond the foreign-made analogues: $A\Pi BBH\Gamma(B)-LS (RU) \cdot A\Pi BBH\Gamma(A)-LS (RU)$ Technical cable requirements correspond to IEC 60840

Cables are used for laying:

- in premises, tunnels, ducts, mines, dry soil and outdoor under shelter
- in bunches

• at sites, where low smoke and gas emission are required (NPP, subway, large industrial facilities, high-rise buildings, etc.)

It is possible to manufacture cables with an integrated fiber-optic module. Order entry example:

АПвЭВнгд-150 1x1600/95 (ОМ) ТУ У 31.3-00214534-060:2011

In conjunction with the DTS system, the integrated fiber-optic module can act as a distributed cable line temperature sensor.

It is possible to manufacture cable with sealed conductor. Order entry example: АПвЭВнгд-150 1x1600/95 (г) ТУ У 31.3-00214534-060:2011

Fire safety code in accordance with ДСТУ 4809:2007: ПБ132121000

Products of this mark meet the requirements:

• single wire cable flame retardance

bunched cable flame retardance category B

• toxicity class Tk2 of the combustion products of nonmetallic elements (toxicity index from 40 up to 120 g/m³)

• class $\protect\ensuremath{\mathcal{I}}\ensuremath{\kappa}\ensuremath{1}$ on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m²/kg)

• class ДПк2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)

• corrosive class K κ 1 of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH less than 4.3, specific conductivity more than 10 μ S/mm)





7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвЭВнгд-150 1x1600 ТУ У 31.3-00214534-060:2011

Power cables with aluminium conductor, flame-retardant, with XLPE and with PVC compound outer sheath and with low smoke and gas emission

TECHNICAL SPECIFICATIONS

Rated voltage	kV	150
Maximum voltage	kV	170
Conductor rated area	mm²	1600
Minimum screen cross-section	mm²	35
Partial discharge factor for rated voltage, not more than	рС	6
Permissible short circuit current across the screen of	kA	14.2
minimum cross-section		
Maximum permissible short-circuit current in core	kA	151
Permissible continious current rating by aerial laying *		
• in trefoil formation with double-side screen earthing	А	1382
• in trefoil formation with single-side screen earthing or	А	1605
cross screen earthing		
plane with double-side screen earthing	А	1265
plane with single-side screen earthing or cross screen	А	1899
earthing		
Permissible continious current rating by burial *		
in trefoil formation with double-side screen earthing	А	955
• in trefoil formation with single-side screen earthing or	А	1153
cross screen earthing		
plane with double-side screen earthing	А	797
plane with single-side screen earthing or cross screen	А	1225
earthing		
Maximum permissible conductor temperature		
Continious	°C	+90
in emergency operation	°C	+130
at short circuit	°C	+250
Operating temperature range (in climate version NF)	°C	-50 +50
Operating temperature range (in climate version T)	°C	-25 +65
Minimum bending radius by laying	mm	1776
Rated outer diameter of the cable (for reference) **	mm	111
Cable weight (approximate)	kg/km	14120
Notes:		

Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

* Long permissible current loads are calculated for the following conditions: conductor temperature 90 °C, air temperature 30 °C, soil temperature 20 °C, load factor 1.0, thermal resistivity of soil 1.0 °K \cdot m/W, laying depth in the ground 1.5 m, while laying in flat formation the distance between cables in clear is equal to the cable diameter, while laying in trefoil formation cables are laid side by side ** The external diameter may differ from the rated up to ± 10 %

*** Отклонение фактической массы брутто от указанного значения может составлять $\pm\,7\,\%$






7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвЭВнгд-150 1x1600 ТУ У 31.3-00214534-060:2011



Power cables with aluminium conductor, flame-retardant, with XLPE and with PVC compound outer sheath and with low smoke and gas emission



CONSTRUCTION

- 1. Aluminium multiwire compacted conductor Notes:
- It is possible to manufacture cable with sealed conductor.
 Conductor segment twisting is not illustrated
- 2. Lapping layer of semiconductive swellable tape
- 3. Inner extruded semiconducting layer
- 4. XLPE insulation
- 5. Outer extruded semiconducting layer
- 6. Lapping layer of semiconductive swellable tape

7. Copper screen

Note: It is possible to manufacture a cable with a fiber optic module built into the screen, including as a DTS system sensor

- 8. Lapping layer of glass tape
- 9. Low fire-risk PVC compound outer sheath