





7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвВГнгд 3x185+1x95 (ож)-1 ТУ У 31.3-00214534-018-2003

Power cables with aluminium conductors, XLPE-insulated, with low fire-risk PVC-compound outer sheath

Cables are used for laying:

- · in bunches
- in premises, dry ducts and tunnels, in corrosive environment
- in bunches, in crowded places

Manufacturing of cable with multiwire conductors (main and additional one) is possible

Fire safety code in accordance with ДСТУ 4809:2007: ΠБ123121000

Products of this mark meet the requirements:

- · single wire cable flame retardance
- bunched cable flame retardance category A
- toxicity class Tk3 of the combustion products of nonmetallic elements (toxicity index over 120 g/m³)
- class ДТк1 on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m²/kg)
- class ДΠκ2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)
- corrosive class Kκ1 of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH less than 4.3, specific conductivity more than 10 μS/mm)

TECHNICAL SPECIFICATIONS

Rated voltage	kV	1
Number and rated area of conductors	mm²	3 x 185 + 1 x 95
Phase insulation thikness	mm	1.6
Permissible continious current rating (AC of industrial frequency) 7	•	
• by aerial laying	Α	382
• by burial	Α	341
Maximum permissible conductor temperature		
Continious	°C	+90
in emergency operation	°C	+130
• at short circuit	°C	+250
Operating temperature range	°C	-50 +50
Minimum bending radius by laying	mm	382.5
Rated outer diameter of the cable (for reference) **	mm	51
Cable weight (approximate)	kg/km	3170
Rated factory cable length and gross weight of the delivery	m, t	# 18: 430 • 1.8
on the drums ***		# 20: 680 • 2.8
Notes		

When ordering it is neccesary to agree the factory length of the product with the manufacturer

^{*} Long permissible current loads are calculated for the following conditions: air temperature plus 25 °C, soil temperature plus 15 °C, thermal resistivity of soil 1.2 °K • m/W, laying depth in the soil 0.7 m

^{**} The external diameter may differ from the rated up to \pm 10 %








7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвВГнгд 3х185+1х95 (ож)-1 ТУ У 31.3-00214534-018-2003

Power cables with aluminium conductors, XLPE-insulated, with low fire-risk PVC-compound outer sheath



CONSTRUCTION

- 1. Aluminium conductor
- 2. XLPE insulation
- 3. Low fire-risk PVC-compound bundle
- 4. PET film winding
- 5. Low fire-risk PVC-compound inner sheath
- 6. Low fire-risk PVC compound outer sheath

Note: Conductor twisting is not illustrated