



7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвЭгаПнг-НF-30 1x120 ТУ У 31.3-00214534-058:2007



Power cables with aluminium conductors, flame-retardant and halogen-free, with XLPE, longitudinal and transverse screen sealing and polymer compound outer sheath

Technical cable requirements correspond to IEC 60502-2

Cables are used for laying:

• in premises, tunnels, ducts, mines, dry soil and outdoor under shelter

• at sites, where low smoke and corrosive gas emission are required (NPP, subway, large industrial facilities, high-rise buildings, etc.)

single laying

It is possible to manufacture cables with extruded semiconductor layer along outer sheath. Order entry example:

АПвЭгаПнг-HF-П-30 1x120/16 ТУ У 31.3-00214534-058:2007

An extruded semiconductor layer along outer sheath ensures the correct testing of cable line with sections of underground laying in polymer pipes.

It is possible to manufacture cables with an integrated fiber-optic module.

Order entry example:

АПвЭгаПнг-HF-30 1x120/16 (ОМ) ТУ У 31.3-00214534-058:2007

In conjunction with the DTS system, the integrated fiber-optic module can act as a distributed cable line temperature sensor.

It is possible to manufacture cable with

Order entry example:

АПвЭгаПнг-HF-30 1x120/16 (ожк) ТУ У 31.3-00214534-058:2007

It is possible to manufacture cable with sealed conductor. Order entry example:

АПвЭгаПнг-HF-30 1x120/16 (г) ТУ У 31.3-00214534-058:2007

It is possible manufacturing of cables in versions (A) and (B), flame-retardant when laying in bunches

Fire safety code in accordance with ДСТУ 4809:2007: ПБ102122000

Products of this mark meet the requirements:

• single wire cable flame retardance

• toxicity class Tk2 of the combustion products of nonmetallic elements (toxicity index from 40 up to 120 g/m^3)

• class $\[mu]T\kappa 1$ on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m²/kg)

• class ДПк2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)

• corrosive class Kk2 of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH more than 4.3, specific conductivity less than 10 μ S/mm)





 7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830

 E-mail: market@yuzhcable.com.ua

АПвЭгаПнг-HF-30 1x120 ТУ У 31.3-00214534-058:2007

Power cables with aluminium conductors, flame-retardant and halogen-free, with XLPE, longitudinal and transverse screen sealing and polymer compound outer sheath

TECHNICAL SPECIFICATIONS

Rated voltage	kV	30
Maximum voltage	kV	36
Number and rated area of conductors	mm²	1 x 120
Insulation thikness	mm	8
Minimum screen cross-section	mm²	16
Permissible short circuit current across the screen of	kA	3.3
minimum cross-section		
Maximum permissible short-circuit current in core	kA	11.3
Permissible continious current rating *		
by aerial laying in trefoil formation	А	324
• by aerial flat laying	А	391
by burial in trefoil formation	А	252
• by burial flat	А	260
Partial discharge factor for rated voltage, not more than	рС	6
Maximum permissible conductor temperature		
Continious	°C	+90
in emergency operation	°C	+130
at short circuit	°C	+250
Operating temperature range	°C	-60 +50
Minimum bending radius by laying	mm	736
Rated outer diameter of the cable (for reference) **	mm	46
Cable weight (approximate)	kg/km	1840
Rated factory cable length and gross weight of the delivery	m, t	# 20аУД-60: 840 • 2.2
on the drums ***		# 22УД-60: 848 • 2.5
Notes:		

Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

* Long permissible current loads are calculated for the following conditions: conductor temperature 90 °C, air temperature 30 °C, soil temperature 20 °C, thermal resistivity of soil 1.5 °K • m/W, laying depth in the soil 0.8 m, while laying in flat formation the distance between cables in clear is equal to the cable diameter, while laying in trefoil formation cables are laid side by side, shields are earthed on both ends of the line

** The external diameter may differ from the rated up to \pm 10 %

*** Отклонение фактической массы брутто от указанного значения может составлять \pm 7 %






7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

АПвЭгаПнг-HF-30 1x120 ТУ У 31.3-00214534-058:2007



Power cables with aluminium conductors, flame-retardant and halogen-free, with XLPE, longitudinal and transverse screen sealing and polymer compound outer sheath



CONSTRUCTION

- 1. Aluminium multiwire compacted conductor
- Notes: • It is possible to manufacture cable with a single-wire conductor • It is possible to manufacture cable with sealed conductor.
- 2. Inner extruded semiconducting layer
- 3. XLPE insulation
- 4. Outer extruded semiconducting layer
- 5. Lapping layer of semiconductive swellable tape
- 6. Copper screen
- 7. Lapping layer of semiconductive swellable tape
- 8. Alumopolymer tape

9. Polymer compound outer sheath:flame-retardant and halogen-free Note: It is possible to manufacture cable with extruded semiconductor layer along outer sheath