

# АПвЭАкПнг-HF-35 1x630 ТУ У 31.3-00214534-058:2007



Single-core power cables with aluminium conductor, flame-retardant and halogen-free, with XLPE, aluminium-wire armoured, with polymer compound outer sheath

Due to non-magnetic armour, cables operate at AC

Technical cable requirements correspond to IEC 60502-2

Cables are used for laying:

- · in places, where small mechanical impacts on cable are possible, including tensile forces
- · in premises, tunnels, ducts, mines, dry soil and outdoor under shelter
- at sites, where low smoke and corrosive gas emission are required (NPP, subway, large industrial facilities, high-rise buildings, etc.)
- · single laying

It is possible to manufacture cables with extruded semiconductor layer along outer sheath.

Order entry example:

АПВЭАкПнг-HF-П-35 1x630/35 ТУ У 31.3-00214534-058:2007

An extruded semiconductor layer along outer sheath ensures the correct testing of cable line with sections of underground laying in polymer pipes.

It is possible to manufacture cables with an integrated fiber-optic module.

Order entry example:

АПвЭАкПнг-HF-35 1x630/35 (ОМ) ТУ У 31.3-00214534-058:2007

In conjunction with the DTS system, the integrated fiber-optic module can act as a distributed cable line temperature sensor.

It is possible to manufacture cable with sealed conductor.

Order entry example:

АПвЭАкПнг-HF-35 1x630/35 (г) ТУ У 31.3-00214534-058:2007

It is possible manufacturing of cables in versions (A) and (B), flame-retardant when laying in bunches

Fire safety code in accordance with ДСТУ 4809:2007: ΠБ102122000

Products of this mark meet the requirements:

- · single wire cable flame retardance
- toxicity class Tk2 of the combustion products of nonmetallic elements (toxicity index from 40 up to 120 g/m³)
- class  $\mu$ TK1 on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m²/kg)
- class ДΠκ2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)
- corrosive class  $K\kappa 2$  of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH more than 4.3, specific conductivity less than 10  $\mu$ S/mm)







7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

## АПвЭАкПнг-HF-35 1x630 ТУ У 31.3-00214534-058:2007

Single-core power cables with aluminium conductor, flame-retardant and halogen-free, with XLPE, aluminium-wire armoured, with polymer compound outer sheath

### **TECHNICAL SPECIFICATIONS**

Rated voltage	kV	35
Maximum voltage	kV	42
Number and rated area of conductors	mm²	1 x 630
Insulation thikness	mm	8.6
Minimum screen cross-section	mm²	35
Permissible short circuit current across the screen of	kA	7.1
minimum cross-section		
Maximum permissible short-circuit current in core	kA	59
Permissible continious current rating *		
by aerial laying in trefoil formation	Α	907
• by aerial flat laying	Α	1001
• by burial in trefoil formation	Α	593
• by burial flat	Α	584
Partial discharge factor for rated voltage, not more than	рС	6
Maximum permissible conductor temperature		
Continious	°C	+90
• in emergency operation	°C	+130
• at short circuit	°C	+250
Operating temperature range	°C	-60 +50
Minimum bending radius by laying	mm	1120
Rated outer diameter of the cable (for reference) **	mm	70
Cable weight (approximate)	kg/km	5880
Rated factory cable length and gross weight of the delivery	m, t	# 25УД-90: 611 • 5.2
on the drums ***		

#### Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

<sup>\*</sup> Long permissible current loads are calculated for the following conditions: conductor temperature 90 °C, air temperature 30 °C, soil temperature 20 °C, thermal resistivity of soil 1.5 °K ⋅ m/W, laying depth in the soil 0.8 m, while laying in flat formation the distance between cables in clear is equal to the cable diameter, while laying in trefoil formation cables are laid side by side, shields are earthed on both ends of the line

<sup>\*\*</sup> The external diameter may differ from the rated up to  $\pm$  10 %

<sup>\*\*\*</sup> Отклонение фактической массы брутто от указанного значения может составлять ± 7 %








7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

## АПвЭАкПнг-HF-35 1x630 ТУ У 31.3-00214534-058:2007

Single-core power cables with aluminium conductor, flame-retardant and halogen-free, with XLPE, aluminium-wire armoured, with polymer compound outer sheath



### **CONSTRUCTION**

- 1. Aluminium multiwire compacted conductor
  Note: It is possible to manufacture cable with sealed conductor.
- 2. Inner extruded semiconducting layer
- 3. XLPE insulation
- 4. Outer extruded semiconducting layer
- 5. Lapping layer of semiconductive swellable tape
- 6. Copper screen
- 7. Lapping layer of nonwoven cloth tape
- 8. Extruded bedding of polyethylene
- 9. Aluminium-wire armour
- 10. Polymer compound outer sheath:flame-retardant and halogen-free Note: It is possible to manufacture cable with extruded semiconductor layer along outer sheath