



7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

# ПвЭгПнг-HF-6 3x50 ТУ У 31.3-00214534-058:2007



Power cables with copper conductors, flame-retardant and halogen-free, with XLPE, longitudinal screen sealing and polymer compound outer sheath

For the cable of this mark correspond the foreign-made analogues: N2XSEH (DE)

Technical cable requirements correspond to IEC 60502-2

Cables are used for laying:

• in premises, tunnels, ducts, mines, dry soil and outdoor under shelter

• at sites, where low smoke and corrosive gas emission are required (NPP, subway, large industrial facilities,

high-rise buildings, etc.)

single laying

It is possible to manufacture cables with extruded semiconductor layer along outer sheath. Order entry example:

ПвЭгПнг-НF-П-6 3х50/16 ТУ У 31.3-00214534-058:2007

An extruded semiconductor layer along outer sheath ensures the correct testing of cable line with sections of underground laying in polymer pipes.

It is possible to manufacture cables with an integrated fiber-optic module.

Order entry example:

ПвЭгПнг-HF-6 3x50/16 (ОМ) ТУ У 31.3-00214534-058:2007

In conjunction with the DTS system, the integrated fiber-optic module can act as a distributed cable line temperature sensor.

It is possible to manufacture cable with sealed conductors. Order entry example:  $\Pi B \Im \Gamma \Pi H \Gamma - H F - 6 3 x 50/16$  ( $\Gamma$ ) TY Y 31.3-00214534-058:2007

It is possible manufacturing of cables in versions (A) and (B), flame-retardant when laying in bunches

Fire safety code in accordance with ДСТУ 4809:2007: ΠБ102122000 Products of this mark meet the requirements:

• single wire cable flame retardance

• toxicity class Tk2 of the combustion products of nonmetallic elements (toxicity index from 40 up to  $120 \text{ g/m}^3$ )

• class  $\square T\kappa 1$  on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m<sup>2</sup>/kg)

• class ДΠκ2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)

• corrosive class Kk2 of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH more than 4.3, specific conductivity less than 10  $\mu$ S/mm)





7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua



# ПвЭгПнг-HF-6 3x50 ТУ У 31.3-00214534-058:2007

Power cables with copper conductors, flame-retardant and halogen-free, with XLPE, longitudinal screen sealing and polymer compound outer sheath

### **TECHNICAL SPECIFICATIONS**

kV	6
kV	7.2
mm²	3 x 50
mm	2.5
mm²	16
kA	3.3
kA	7.2
А	204
А	181
рС	6
°C	+90
°C	+130
°C	+250
°C	-60 +50
mm	784
mm	49
kg/km	3400
m, t	# 22УД-60: 661 • 3.2
	# 20аУД-60: 810 • 3.5
	# 25УД-90: 1323 • 6.1
	kV mm² mm kA kA kA kA C C °C °C °C °C °C mm mm kg/km

Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

\* Long permissible current loads are calculated for the following conditions: conductor temperature 90 °C, air temperature 30 °C, soil temperature 20 °C, load factor 1.0, thermal resistivity of soil 1.5 °K • m/W, laying depth in the ground 0.8 m, shields are grounded at both ends of the line

\*\* The external diameter may differ from the rated up to  $\pm$  10 %

\*\*\* Отклонение фактической массы брутто от указанного значения может составлять  $\pm$  7 %






7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

## ПвЭгПнг-HF-6 3x50 ТУ У 31.3-00214534-058:2007

Power cables with copper conductors, flame-retardant and halogen-free, with XLPE, longitudinal screen sealing and polymer compound outer sheath



### **CONSTRUCTION**

- 1. Copper multiwire compact conductor
- Note: It is possible to manufacture cable with sealed conductors. 2. Inner extruded semiconducting layer
- 3. XLPE insulation
- 4. Outer extruded semiconducting layer
- 5. Lapping layer of semiconductive swellable tape
- 6. Copper screen
- 7. Extruded filling of PVC compound

8. Polymer compound outer sheath:flame-retardant and halogen-free Note: It is possible to manufacture cable with extruded semiconductor layer along outer sheath

Note: Conductor twisting is not illustrated

0 10 20 30 40