



7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

# АПвЭгПнг-150 1x630 ТУ У 31.3-00214534-060:2011



Power cables with aluminium cunductor, flame-retardant, with XLPE, longitudinal screen sealing and polymer compound outer sheath

For the cable of this mark correspond the foreign-made analogues: XnUHAKXS (PL)

Technical cable requirements correspond to IEC 60840

Cables are used for laying:

- in premises, tunnels, ducts, mines, dry soil and outdoor under shelter
- single laying

It is possible to manufacture cables with extruded semiconductor layer along outer sheath. Order entry example:

АПвЭгПнг-П-150 1х630/95 ТУ У 31.3-00214534-060:2011

An extruded semiconductor layer along outer sheath ensures the correct testing of cable line with sections of underground laying in polymer pipes.

It is possible to manufacture cables with an integrated fiber-optic module.

Order entry example:

АПвЭгПнг-150 1x630/95 (ОМ) ТУ У 31.3-00214534-060:2011

In conjunction with the DTS system, the integrated fiber-optic module can act as a distributed cable line temperature sensor.

It is possible to manufacture cable with sealed conductor. Order entry example:

АПвЭгПнг-150 1х630/95 (г) ТУ У 31.3-00214534-060:2011

Fire safety code in accordance with ДСТУ 4809:2007: ПБ121122000

Products of this mark meet the requirements:

• single wire cable flame retardance

bunched cable flame retardance category A

• toxicity class Tk1 of the combustion products of nonmetallic elements (toxicity index from 13 up to 40 g/m<sup>3</sup>)

• class  $\mathcal{A}T\kappa 1$  on smoke-forming ability by smouldering of non-metallic elements (coefficient of smoke formation from 50 to 500 m<sup>2</sup>/kg)

• class ДΠк2 on smoke-forming ability by combustion (minimum luminous flux more than 60 %)

• corrosive class Kk2 of combustion products of non-metallic elements (the number of halogen hydrides less than 150 mg/g, pH more than 4.3, specific conductivity less than 10  $\mu$ S/mm)





7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

## АПвЭгПнг-150 1x630 ТУ У 31.3-00214534-060:2011

Power cables with aluminium cunductor, flame-retardant, with XLPE, longitudinal screen sealing and polymer compound outer sheath

## **TECHNICAL SPECIFICATIONS**

Rated voltage	kV	150
Maximum voltage	kV	170
Conductor rated area	mm²	630
Minimum screen cross-section	mm²	35
Partial discharge factor for rated voltage, not more than	pC	6
Permissible short circuit current across the screen of	kA	7.1
minimum cross-section		
Maximum permissible short-circuit current in core	kA	59
Permissible continious current rating by aerial laying *		
in trefoil formation with double-side screen earthing	Α	810
in trefoil formation with single-side screen earthing or	Α	855
cross screen earthing		
plane with double-side screen earthing	Α	809
plane with single-side screen earthing or cross screen	Α	992
earthing		
Permissible continious current rating by burial *		
in trefoil formation with double-side screen earthing	Α	627
• in trefoil formation with single-side screen earthing or	А	672
cross screen earthing		
plane with double-side screen earthing	А	576
plane with single-side screen earthing or cross screen	А	707
earthing		
Maximum permissible conductor temperature		
Continious	°C	+90
in emergency operation	°C	+130
at short circuit	°C	+250
Operating temperature range	°C	-60 +50
Minimum bending radius by laying	mm	1392
Rated outer diameter of the cable (for reference) **	mm	87
Cable weight (approximate)	kg/km	9260
Rated factory cable length and gross weight of the delivery	m, t	# 25УД-90: 396 • 5.2
on the drums ***		# 26УД-100: 457 • 6.1
		# 30УД-130: **** 772 • 10.0

#### Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

\* Long permissible current loads are calculated for the following conditions: conductor temperature 90 °C, air temperature 30 °C, soil temperature 20 °C, load factor 1.0, thermal resistivity of soil 1.0 °K  $\cdot$  m/W, laying depth in the ground 1.5 m, while laying in flat formation the distance between cables in clear is equal to the cable diameter, while laying in trefoil formation cables are laid side by side \*\* The external diameter may differ from the rated up to ± 10 %

\*\*\* Отклонение фактической массы брутто от указанного значения может составлять ± 7 %

\*\*\*\* Option delivery on not full drum






7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

# АПвЭгПнг-150 1x630 ТУ У 31.3-00214534-060:2011



Power cables with aluminium cunductor, flame-retardant, with XLPE, longitudinal screen sealing and polymer compound outer sheath



## CONSTRUCTION

- **1. Aluminium multiwire compacted conductor** Note: It is possible to manufacture cable with sealed conductor.
- 2. Inner extruded semiconducting layer
- 3. XLPE insulation
- 4. Outer extruded semiconducting layer
- 5. Lapping layer of semiconductive swellable tape

### 6. Copper screen

Note: It is possible to manufacture a cable with a fiber optic module built into the screen, including as a DTS system sensor

7. Lapping layer of glass tape

#### 8. Flame-retardant polymer compound outer sheath

Note: It is possible to manufacture cable with extruded semiconductor layer along outer sheath