



СИПН-4 1x50 ДСТУ 4743:2007, ТУ У 27.3-00214534-079:2014

Self-supporting flame-retardant wires with polymer compound insulation

Used for laying:

- *aerial electric power lines for the rated voltage of 0.6/1 kV*
- *branches from aerial electric power lines for the rated voltage of 0.6/1 kV to the input and for the laying on the walls of buildings and engineering structures*
- *in air, types II and III according to ГОСТ 15150-69*

It is possible to manufacture the wire with longitudinal core sealing by water-blocking materials

Fire safety code in accordance with ДСТУ 4809:2007: ПБ100000000

Products of this mark meet the requirements:

- *single wire cable flame retardance*

TECHNICAL SPECIFICATIONS

Rated voltage	kV	0.6 / 1
Number and rated area of phase conductors	mm ²	1 x 50
Phase insulation thickness	mm	1.5
Current ratings *		
• <i>Continuous</i>	A	195
• <i>at short circuit (not more than 1 s)</i>	kA	4.6
Maximum permissible conductor temperature		
• <i>Continuous</i>	°C	+90
• <i>at short circuit (not more than 5 s)</i>	°C	+250
Operating temperature range	°C	-60 ... +50
Permissible temperature of laying (installation), no less than	°C	-20
Minimum bending radius by laying	mm	110
Rated outer diameter of the cable (for reference) **	mm	11
Weight (approximate)	kg/km	170
Rated factory cable length and gross weight of the delivery on the drums ***	m, t	# 16a: 8360 • 1.7

Notes:

When ordering it is necessary to agree the factory length of the product with the manufacturer

** Long permissible current loads are calculated for the following conditions: ambient temperature plus 25 °C, wind speed 0.6 m/s, the intensity of solar radiation 1000 W/m²*

*** The external diameter may differ from the rated up to ± 10 %*



СИПН-4 1x50 ДСТУ 4743:2007, ТУ У 27.3-00214534-079:2014

Self-supporting flame-retardant wires with polymer compound insulation

CONSTRUCTION

1. Aluminium multiwire compacted conductor

Note: It is possible to manufacture the wire with longitudinal core sealing by water-blocking materials

2. Flame-retardant polymer compound insulation

