





7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

AsXSn 4x16 Ty y 27.3-00214534-074:2013

Self-supporting flame-retardant wires with polymer compound insulation

Used for laying:

- aerial electric power lines for the rated voltage of 0.6/1 kV
- · branches to the inputs into dwellings and outbuildings

It is possible to manufacture the wire with longitudinal core sealing by water-blocking materials

Fire safety code in accordance with ДСТУ 4809:2007: ΠБ100000000 Products of this mark meet the requirements:

· single wire cable flame retardance

TECHNICAL SPECIFICATIONS

Rated voltage	kV	0.6 / 1
Number and rated area of phase conductors	mm²	4 x 16
Phase insulation thikness	mm	1.4
Current ratings *		
Continious	Α	100
• at short circuit (not more than 1 s)	kA	1.5
Maximum permissible conductor temperature		
Continious	°C	+90
• at short circuit (not more than 5 s)	°C	+250
Operating temperature range	°C	-60 +50
Permissible temperature of laying (installation), no less than	°C	-20
Minimum bending radius by laying	mm	181
Rated outer diameter of the cable (for reference) **	mm	18.1
Weight (approximate)	kg/km	280
Rated factory cable length and gross weight of the delivery	m, t	# 16a: 3120 · 1.1
on the drums ***		# 18: 3570 • 1.5
		# 20: 5710 • 2.2

Notes:

When ordering it is neccesary to agree the factory length of the product with the manufacturer

^{*} Long permissible current loads are calculated for the following conditions: ambient temperature plus 25 °C, wind speed 0.6 m/s, the intensity of solar radiation 1000 W/m²

^{**} The external diameter may differ from the rated up to \pm 10 %







7, Autogennaya Str., Kharkov, 61099, Ukraine. Phone: (+38-057) 728-1244, 728-1241. Fax: (+38-057) 728-1243, (+38-0572) 946-830 E-mail: market@yuzhcable.com.ua

AsXSn 4x16 ТУ У 27.3-00214534-074:2013

Self-supporting flame-retardant wires with polymer compound insulation

CONSTRUCTION

1. Aluminium multiwire compacted conductor
Note: It is possible to manufacture the wire with longitudinal core sealing by water-blocking

2. Flame-retardant polymer compound insulation

Note: Wire lay-up is not illustrated.

