



AA_sXSn-35 1x240

TY Y 27.3-00214534-072:2013

Single-core self-supporting high-voltage flame-retardant wires with polymer compound insulation

Used for laying:

- *aerial electric power lines for the rated voltage from 10 kV till 35 kV*
- *in air, types II and III according to ГOCT 15150-69, including on sea coasts, salt lakes, in industrial areas and areas of saline sands*

It is possible to manufacture the wire with longitudinal core sealing by water-blocking materials

Fire safety code in accordance with ДСТУ 4809:2007: ПБ100000000

Products of this mark meet the requirements:

- *single wire cable flame retardance*

TECHNICAL SPECIFICATIONS

Rated voltage	kV	35
Number and rated area of phase conductors	mm ²	1 x 240
Phase insulation thickness	mm	3.5
Current ratings *		
• <i>Continuous</i>	A	670
• <i>at short circuit (not more than 1 s)</i>	kA	20.6
Maximum permissible conductor temperature		
• <i>Continuous</i>	°C	+90
• <i>at short circuit (not more than 5 s)</i>	°C	+250
Operating temperature range	°C	-60 ... +50
Permissible temperature of laying (installation), no less than	°C	-20
Minimum bending radius by laying	mm	253
Rated outer diameter of the cable (for reference) **	mm	25.3
Weight (approximate)	kg/km	880
Rated factory cable length and gross weight of the delivery on the drums ***	m, t	# 16a: 1500 • 1.6 # 18: 1710 • 2.0 # 20: 2740 • 3.1

Notes:

When ordering it is necessary to agree the factory length of the product with the manufacturer

** Long permissible current loads are calculated for the following conditions: ambient temperature plus 25 °C, wind speed 0.6 m/s, the intensity of solar radiation 1000 W/m²*

*** The external diameter may differ from the rated up to ± 10 %*



AA sXS n-35 1x240
TY Y 27.3-00214534-072:2013

Single-core self-supporting high-voltage flame-retardant wires with polymer compound insulation



CONSTRUCTION

1. Multiwire aluminium-alloy compacted conductor

Note: It is possible to manufacture the wire with longitudinal core sealing by water-blocking materials

2. Flame-retardant polymer compound insulation